






Adhesives Product Sales Sheet

Product	Available In	Type	Works With	Maximum RH (per ASTM F-2170)	Substrate pH	Flash Time	Working Time	Shelf Life	Freeze/ Thaw Stability	Antimicrobial	Trowel	Spread Rate
 E-Grip III	4 Gallon Pail 28 oz Cartridge*	One-Part Urethane	Vulcanized Composition Rubber	85%	7-9	None	30-45 minutes	1 Year	Stable	Yes	1/16" x 1/32" x 1/32" U-notch	140 SF/gal
											1/16" sq. notch	95 SF/gal
											1/8" sq. notch	60 SF/gal
 E-Grip 95	4 Gallon Pail	One-Part Urethane	Vulcanized Composition Rubber	95%	Max of 12	None	30-45 minutes	1 Year	Stable	Yes	1/16" x 1/32" x 1/32" U-notch	160 SF/gal
											1/16" sq. notch	115 SF/gal
 E-Grip 99	4 Gallon Pail	One-Part Modified Urethane	Vulcanized Composition Rubber	99%	5 to 14	LVT: 10-15 minutes All other products: None	45 minutes	1 Year	Stable to 10°F (-12°C)	Yes	1/16" x 1/32" x 1/32" U-notch (LVT/LVP only)	135 SF/gal
			Vinyl and LVT over Concrete (not over rubber)								1/16" sq. notch	105 SF/gal
 E-TAK 99	4 Gallon Pail	One-Part Acrylic PSA	LVT, 2mm Sheet Vinyl, Sound Control Underlayments	Tacky (Pressure Sensitive Installations) LVT Only				1 year when stored in original/unopened packaging at 73°F (23°C)	Protect from Freezing	Yes	Porous/Rough Substrate	
				99%	≤12	30-60 minutes	Up to 4 hours				1/16" sq. notch	150 SF/gal
				Wet/Semi-Wet Adhesive Installations							Non-Porous/Smooth Substrate	
				95%	≤11	N/A	Up to 30 minutes				1/16" x 1/32" x 1/32" U-notch	210 SF/gal
 E-Grip Tape	29" x 131' Roll	Tape	Products under 8.5mm	80%	7-9	N/A	N/A	2 years from Ecore ship date	N/A	No	N/A	322 SF/roll

For more information, see the Technical Data Sheet on the specific adhesive product pages at ecoreintl.com.

*One 28 oz cartridge of E-Grip III is required for every 40 Quad Blok (1" Tiles) or for every 28 Quad Bloks (2.5" Tiles)

Adhesive Comparison Matrix

	E-Grip III	E-Grip 95	E-Grip 99	E-Grip Tape	E-TAK 99
ph and RH	★☆☆	★★★	★★★	★☆☆	★★★
Trowelable	★☆☆	★★★	★★★	N/A	★★★
Weighting of Seams (★☆☆ = seams need weighted)	★★★	★☆☆	★☆☆	★★★	★★★
Open Time	★★★	★★★	★★★	N/A	★★★
Working Time	★★★	★★★	★★★	N/A	★★★
Initial "Green" Strength	★★★	★☆☆	★☆☆	★★★	★★★
Light Foot Traffic (24 Hours)	★★★	★★★	★★★	★★★ Immediately	★★★
Heavy Foot Traffic (48 Hours)	★★★	★★★	★★★	★★★ Immediately	★★★
Heavy Rolling Loads (72 Hours)	★★★	★★★	★★★	★★★ Immediately	★★★